

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE

Modena, 27/02/18

To **CERAMIKA NOWA GALA S.A.**  
UL. CERAMICZNA 1  
26-200 KONSKIE PL

Attn. **Ewelina Stepien**

MATERIAL and/or SAMPLE to be tested	Denomination of the Sample	Client Reference – Your delivery	date
porcelain tiles	MONDO 33X33	your delivery	15/02/2018

Here attached, you will receive the Test Report of Serial No. **20181226**/n, which shows the results of tests required.

**MODENA CENTRO PROVE**

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe



**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

## TEST REPORT: 20181226/1

Modena, 27/02/18

<b>CUSTOMER</b>	<b>CERAMIKA NOWA GALA S.A. - - UL. CERAMICZNA 1 - 26-200 - KONSKIE - PL</b>
<b>MATERIAL and/o SAMPLE to be tested</b>	porcelain tiles;
<b>Denomination</b>	MONDO 33X33;
<b>Date of sample reception</b>	15/02/2018;
<b>Kind of test executed</b>	Determination of the Anti-Slip characteristics
<b>Referring standards</b>	DIN 51130:2014
<b>Shifting from standards</b>	No one
<b>Equipment</b>	Pullmeter with ramp cod. MCP C150
<b>Calibration</b>	RT 01 of 30/08/2017
<b>Subcontracted phases</b>	No one
<b>Sampling made by</b>	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.  
The times of retain of the samples was indicated in the offer related to the test report.*

<b>Examiner</b>  p.i. Bortolai Alberto	<b>Examiner</b>  p.i. Nasseti Luca	<b>MODENA CENTRO PROVE</b>  Ceramic Dept. Responsible P.I. De Pasquale Roberto	<b>MODENA CENTRO PROVE</b>  Director Sant'Unione dr. Giuseppe
--	--	---	--

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

**DETERMINATION OF THE ANTI-SLIP CHARACTERISTICS**

Beginning date : 15/02/2018

Analysis ending date : 16/02/2018

**SAMPLE** : Ceramic tiles, marked « **MONDO 33X33** »

The test regards the working areas with a high slipping risk: the procedure foresees that a person taking part in the test walks on an inclined plane which is floored with the tested tiles and greased an oil whose viscosity is SAE 10W-30. During the execution of the test it is determined if the tested material may be properly laid down in specific work environments.

There is an average inclination which determines the insecurity of the person walking on the inclined plane and causes the classification of the tested tiles in one of five groups used to determine the sliding resistance.

**RESULTS**

- Mean inclination angle  $\alpha_{ges}$  : 23.6°
- Classification : R 11

**CLASSIFICATION**

Mean value $\alpha_{ges}$	Class
$6^\circ \leq \alpha_{ges} \leq 10^\circ$	R 9
$10^\circ < \alpha_{ges} \leq 19^\circ$	R 10
$19^\circ < \alpha_{ges} \leq 27^\circ$	R 11
$27^\circ < \alpha_{ges} \leq 35^\circ$	R 12
$\alpha_{ges} > 35^\circ$	R 13

**Note** : The group classification give the parameter for determine the sliding resistance: the group R 9 is less anti-slip, the group R 13 as the maximum effectiveness anti-slip.

<b>Examiner</b>  p.i. Bortolai Alberto	<b>Examiner</b>  p.i. Nasseti Luca	<b>MODENA CENTRO PROVE</b>  Ceramic Dept. Responsible P.I. De Pasquale Roberto	<b>MODENA CENTRO PROVE</b>  Director Sant'Unione dr. Giuseppe
--	--	---	--